





TABELLA DI CONVERSIONE DEI CAVI COMPENSATI DI ESTENSIONE PER TERMOCOPPIA

TIPO TERMOCOPPIA / THERMOCOUPLE TYPE		USA ANSI MC96.1	D DIN	GB BS	F NFE	EUROPE IEC / CEI
J	FERRO (magnetico) RAME-NICKEL * IRON CONSTANTAN					
K	NICKEL-CROMO NICKEL-ALLUMINIO CHROMEL ALUMEL					
W	FERRO (magnetico) RAME-NICKEL IRON COPPER-NICKEL					
V	RAME RAME-NICKEL * COPPER CONSTANTAN					
R (13%) S (10%)	RAME RAME-NICKEL COPPER COPPER-NICKEL					
T	RAME RAME-NICKEL * COPPER CONSTANTAN					
E	NICKEL-CROMO RAME-NICKEL * CHROMEL CONSTANTAN					
B	RAME RAME COPPER COPPER					

(*) Rame-Nickel = Costantana - Copper-Nickel = Constantan